

CUP 700

Copper - Phosphorus

Mechanical & Physical Properties

Melting Range	C°	710-805
Recommended Working Temperature	C°	730
Tensile Strength	Mpa	
Electrical Conductivity	% IACS	7,5
Density	gr/cm ³	7,9
Elongation	%	

Specifications

EN ISO 17672		CuP 180
DIN 8513		L-CuP7
AWS A5.8		BCuP-2
DIN EN 1044		CP 202
EN ISO 3677		B-Cu93P-710/805

Main elements %(min-max)

P: 6,8-7,2 / Cu: Bal.

Other %

Impurity : 0,25 max

RoHS Limit ppm

Cd (100ppm) ; Pb / Hg / Cr (1000ppm)

Availability

Bare rods	Coated Rods	Wire / Coil	Foil	Preforms	Powder	Paste	Flexible Wire
●	○	●	○	○	○	○	●

Liability - Disclaimer: This document is intended to assist the user in choosing the product. We provide these results in all conscience; this not however exempting the consumer from the obligation to check our products and process on his own responsibility, including suitability, compliance with applicable law and non-infringement of the rights of others. The company ASA KAYNAK cannot be held liable in respect thereof.

ASA KAYNAK ve METAL ALAŞIMLARI SAN. ve TİC. A.Ş.

Veliköy OSB Sanayi Mahallesi 22. Cad. 4/A
Veliköy / Çerkezköy / Tekirdağ / Turkey 59500
Phone: +90 282 746 1004

www.asakaynak.com

info@asakaynak.com