

TDS n°94 Rev n°2 04/05/2017 Date of Edition: 12/13/2025

K 500 Silver Brazing Alloys Cadmium Bearing

Mechanical & Physical Properties							
Melting Range	C°	620/640					
Recommended Working Temperature	C°	640					
Tensile Strength	Мра	-					
Electrical Conductivity	% IACS	23,9					
Density	gr/cm³	9,45					
Elongation	%	-					

Specifications	
EN ISO 17672	Ag 350
DIN 8513	L-Ag50Cd
AWS A5.8	BAg-1a
DIN EN 1044	AG 301
EN ISO 3677	B-Ag50CdZnCu-620/640

Main elements %(min-max)

Ag: 49-51 / Cd: 17-19 / Zn: 14,5-18,5 / Cu: 14,5-16,5

Other %

Impurity: 0,15 max

Elongation %

RoHS Limit ppm N/A

Availability							
Bare rods	Coated Rods	Wire / Coil	Foil	Preforms	Powder	Paste	Flexible Wire
•	•	•	•	•	0	0	•

Liability - Disclaimer: This document is intended to assist the user in choosing the product. We provide these results in all conscience; this not however exempting the consumer from the obligation to check our products and process on his own responsibility, including suitability, compliance with applicable law and non-infringement of the rights of others. The company ASA KAYNAK cannot be held liable in respect thereof.

ASA KAYNAK ve METAL ALAŞIMLARI SAN. ve TİC. A.Ş.

Veliköy OSB Sanayi Mahallesi 22. Cad. 4/A Veliköy / Çerkezköy / Tekirdağ / Turkey 59500 Phone: +90 282 746 1004