TECHNICAL DATA SHEET

TDS 32 Rev n°1 23/08/2016 Date of Edition: 12/15/2025

CUP 606 Copper - Phosphorus

Mechanical & Physical Properties							
Melting Range	C°	710-825					
Recommended Working Temperature	C°	730					
Tensile Strength	Мра						
Electrical Conductivity	% IACS						
Density	gr/cm³						
Elongation	%						

Specifications	
EN ISO 17672	CuP 180
DIN 8513	L-CuP7
AWS A5.8	
DIN EN 1044	CP 202
EN ISO 3677	B-Cu93P-710/825
	·

Main elements % (min-max)

P: 6,4-6,8 / Cu: Bal.

Other %

Impurity: 0,25 max

RoHS Limit ppm

Cd (100ppm); Pb / Hg / Cr (1000ppm)

Availability							
Bare rods	Coated Rods	Wire / Coil	Foil	Preforms	Powder	Paste	Flexible Wire
•	0	•	0	0	0	0	•

Liability - Disclaimer: This document is intended to assist the user in choosing the product. We provide these results in all conscience; this not however exempting the consumer from the obligation to check our products and process on his own responsibility, including suitability, compliance with applicable law and non-infringement of the rights of others. The company ASA KAYNAK cannot be held liable in respect thereof.

ASA KAYNAK ve METAL ALAŞIMLARI SAN. ve TİC. A.Ş.

Veliköy OSB Sanayi Mahallesi 22. Cad. 4/A Veliköy / Çerkezköy / Tekirdağ / Turkey 59500 Phone: +90 282 746 1004