

TDS 37 Rev n°1 23/08/2016 Date of Edition: 11/4/2025

CUP 618 SFSpark Free Copper - Phosphorus

Mechanical & Physical Properties							
Melting Range	C°	710-815					
Recommended Working Temperature	C°	730					
Tensile Strength	Мра						
Electrical Conductivity	% IACS						
Density	gr/cm³						
Elongation	%						

Specifications						
EN ISO 17672		CuP 180				
DIN 8513		L-CuP7				
AWS A5.8						
DIN EN 1044		CP 202				
EN ISO 3677		B-Cu93P-710/815				

Main elements %(min-max)

P: 6,6-7,0 / Cu: Bal.

Other %

Impurity: 0,25 max

RoHS Limit ppm

Cd (100ppm); Pb / Hg / Cr (1000ppm)

Availability							
Bare rods	Coated Rods	Wire / Coil	Foil	Preforms	Powder	Paste	Flexible Wire
•	0	•	0	0	0	0	•

Liability - Disclaimer: This document is intended to assist the user in choosing the product. We provide these results in all conscience; this not however exempting the consumer from the obligation to check our products and process on his own responsibility, including suitability, compliance with applicable law and non-infringement of the rights of others. The company ASA KAYNAK cannot be held liable in respect thereof.

ASA KAYNAK ve METAL ALAŞIMLARI SAN. ve TİC. A.Ş.